


Specification Sheet

CK - 60



Plastic Optical Fiber

ESKA

High - Performance Plastic Optical Fiber

E s k a[™]


1.Scope

2. Structure

Table1

		CK - 60			
Item		Specification			
		Unit	Min.	Typ.	Max.
Optical Fiber	Core Material	—	Polymetyl - Methacrylate Resin		
	Cladding Material	—	Fluorinated Polymer		
	Core Refractive Index	—	1.49		
	Numerical Aperture	—	0.5		
	Refractive Index Profile	—	Step Index		
	Core Diameter	μm	1,380	1,470	1,560
	Cladding Diameter	μm	1,410	1,500	1,590
Approximate Weight		g / m	2.2		

Sectional View



3.Performance

Item		Acceptance Criterion and / or [Test Condition]	CK - 60			
			Specification			
			Unit	Min.	Typ.	Max.
Maximum Rating	Storage and Operation Temperature	No Deterioration in Optical Properties*	°C	- 55	—	+ 70
	Operation Temperature under high humidity	No Deterioration in Optical Properties** [95 %RH]	°C	-	—	+ 60
Optical Properties	Transmission Loss	650 nm Collimated Light] [Standard condition] [10 m - 1 m cutback]	dB/km	—	—	200
Mechanical Characteristics	Minimum Bend Radius	Loss Increment =< 0.5 dB [Quarter bend]	mm	30	—	—
	Tensile Strength	[Tensile Force at Yield Point] [JIS C 6861]	N	126	—	—

All tests are carried out under temperature of 25°C unless otherwise specified.

* Attenuation change shall be within 10 % after 1,000 hours.

** Attenuation change shall be within 10 % after 1,000 hours, except that due to absorbed water .

The specification is subject to change without notice.

The information contained herein is presented as a guide for the product selection. Please contact our business department for the issue of an official specification sheet.